

Marking of components	Material / product name	Technical data / Dimension weight / strength	Producer
Attachement loops	Nylon	7,2 g/m / breaking strength 110 kg / 13 mm spreads	Kolon Industrial Co, Korea
Accelerator lines	Nylon	Ø 4,0 mm = breaking strength 350 daN	
Accelerator - brakeroll	GIN Rolle		Gin Glider Korea
Accelerator lock	Brummelhook		Gin Glider Korea
brake attachements	Nylon	7,2g/m breaking strength 110 kg / 13mm spreads	Kolon Industrial Co, Korea
brake handhold	High Tanacity Poliester Yam 22mm	25 g/m / 1000 kg breaking strength	Techni Sangles, France
brake handhold attachment	High Tanacity Poliester Yam 22mm	25 g/m / 1000 kg breaking strength	Techni Sangles, France
brake handholde attachment	Magnet		Gin Glider Korea
Break main line 2,3 mm Ø	Dynema Lines	2,3 mm = 250 daN	Gin Teijin Korea
Lines: DC60, DSL 70, PSSL 120, 160, 200, 275	Liros Lines		Rosenberger Tauwerke Gin Gliders Korea
belt direction	Stainless Steel	8g/Ø 3,8 mm / breaking strength 800kg	Ansung Precision CO. Korea
lines lock	Stainless Steel	12g / Ø4,3 mm / breaking strength 1000kg	Ansung Precision CO. Korea
Top sai -A-B-C	Skytex 36 / Skytex 27	36 g/m ² / 27g/m ² (PA 6,6 HT)	Porcher Marine, NCV, France
V-Tape	Skytex 27	27 g/m ² (PA 6,6 HAT)	Paratex, Germany
Nose reinforcement	P 260	283 g/m ²	Dimension-Polyant, Germany
Rips, Profile	Skytex 36 / Skytex 27	36 g/m ² / 27g/m ² (PA 6,6 HT)	Paratex, Korea
Riser	High Tanacity Poliester Yam 22mm	25 g/m / 1000 kg breaking strength	Techni Sangles, France
Bottom sail - A-B-C	Skytex 27	27 g/m ² (PA 6,6 HT)	Porcher Marine, NCV, France
Reinforcement pivot point B/C/D	W 420	180 g/m ²	Porcher Marine, NCV, France
sewing thread canopy	High Tanacity Poliester Yam 150 D/2	0,05 g/m ² / 2,9 kg breaking strength	Amann & Söhne GmbH, Germany
sewing thread lines	High Tanacity Poliester Yam 150 D/3	0,083 g/m ² / 3,2 kg breaking strength	Amann & Söhne GmbH, Germany